

Amendments to the SpecificationIN THE WRITTEN DESCRIPTION

Please replace Table 3 on page 19, with the following rewritten Table 3:

Table 3

Product Name	Manufacturer	Parts by weight				
		Ex. 3	Ex. 4	Ex. 5	Comp. Ex. 3	Comp. Ex. 4
NBR polymer N240S *1	JSR Co., Ltd.	100	100	100	100	100
Stearic acid	NOF Corp.	1	1	1	1	1
PEG #4000	NOF Corp.	1	1	1	1	1
Nipsil VN3 *2	Nippon Silica Co., Ltd.	±5	±0	±5	±0	±0
Novelight A	Nitto Funka Ind. Co., Ltd.	72	0	0	72	0
Tamapearl TP-123	Okutama Ind. Co., Ltd.	0	72	72	0	0
Hakuenka CC	Shiraishi Corp.	0	0	0	0	72
R-650	Sakai Chem. Ind. Co., Ltd.	26	26	26	26	26
Nocrac	Ouchishinko Chemical Industrial Co., Ltd.	1	1	1	1	1
DIDP	Kyowa Hakko Kogyo Co., Ltd.	20	20	20	20	20
Nyper BW *3	NOF Corp.	2.5	2.5	2.5	2.5	2.5
Perhexa 25B-40 *4	NOF Corp.	2.5	2.5	2.5	2.5	2.5
Neocellborn N1000S *5	Eiwa Chemical Ind. Co., Ltd.	5.0	5.0	5.0	5.0	5.0
VESTA-18	Inoue Sekkai Ind. Co., Ltd.	5.0	5.0	5.0	5.0	5.0

Note \*1: NBR polymer

\*2: white filler

\*3: low temperature crosslinking agent

\*4: high temperature crosslinking agent

\*5: blowing agent